



RL22500DG (2V2500Ah)

RL22500DG is GEL Deep cycle battery superiorly designed for frequent cyclic discharge applications under extreme temperature. By using strong grid to insure reliable performance under frequent cyclic discharge use. 400 cycles could be available at 100% DOD. Offering extra-durable cyclic performance, high efficiency of recovery ,that is more suitable for solar, mobility, E-toll, marine , deep discharge UPS etc..



Specification

Cells Per Unit	1
Voltage Per Unit	2
Capacity	2500Ah@20hr-rate to 1.75V per cell @25°C
Weight	Approx. 171.0 Kg
Max. Discharge Current	25000 A (5 sec)
Internal Resistance	Approx. 0.3 mΩ
Operating Temperature Range	Discharge: -40°C~60°C Charge: -20°C~50°C Storage: -40°C~60°C
Normal Operating Temperature Range	25°C±5°C
Float charging Voltage	2.27 to 2.3 VDC/unit Average at 25°C
Recommended Maximum Charging Current Limit	500A
Equalization and Cycle Service	2.37 to 2.4 VDC/unit Average at 25°C
Self Discharge	RITAR Valve Regulated Lead Acid (VRLA) batteries can be stored for more than 6 months at 25°C. Self-discharge ratio less than 3% per month at 25°C. Please charge batteries before using.
Terminal	Terminal F10
Container Material	A.B.S. (UL94-HB), Flammability resistance of UL94-V1 can be available upon request.



MH28539




G4M20206-0910-E-16



ISO9001:2000 Certificate

Dimensions

Unit: mm Dimension: 712(L)×351(W)×338(H) Terminal F10



Constant Current Discharge Characteristics: A (25°C)


F.V/Time	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	6HR	8HR	10HR	20HR
1.60V	3055	2366	1522	904.9	674.0	537.3	452.5	380.0	306.8	256.4	132.0
1.65V	2905	2271	1456	871.9	645.7	518.5	433.6	370.9	293.0	247.2	127.3
1.70V	2709	2141	1428	857.8	631.6	513.7	428.9	361.7	288.4	242.7	125.0
1.75V	2405	1903	1315	810.7	598.6	485.5	410.0	343.4	279.3	238.1	122.6
1.80V	2070	1755	1240	773.0	575.0	480.7	395.9	338.8	274.7	228.9	117.9
1.85V	1751	1580	1145	730.5	546.7	443.0	377.1	320.5	261.0	219.8	113.2

Constant Power Discharge Characteristics: W (25°C)


F.V/Time	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	6HR	8HR	10HR	20HR
1.60V	5348	4206	2720	1635	1225	985.1	834.2	718.8	572.3	485.3	249.9
1.65V	5208	4184	2710	1612	1221	975.6	824.8	709.7	567.7	480.7	247.6
1.70V	4920	3892	2625	1588	1183	961.5	815.4	695.9	558.6	476.2	245.2
1.75V	4382	3506	2451	1518	1141	928.5	782.4	663.9	544.8	462.4	238.2
1.80V	3793	3232	2309	1452	1093	900.2	758.8	650.2	526.5	448.7	231.1
1.85V	3235	2913	2130	1367	1042	829.5	725.8	613.5	503.6	435.0	224.0

All mentioned values are average values.

Life characteristics of cyclic use




Storage characteristic



Charge characteristic curve for cyclic use



Discharge characteristic curve



Capacity Factors With Different Temperature

Battery Type		-20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
GEL Battery	6V&12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%
	2V	60%	75%	85%	88%	92%	99%	100%	103%	105%	106%
AGM Battery	6V&12V	46%	66%	76%	83%	90%	98%	100%	103%	107%	109%
	2V	55%	70%	80%	85%	92%	99%	100%	104%	108%	110%

Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75V	1.70V	1.60V
Discharge Current (A)	(A) ≤ 0.2C	0.2C < (A) < 1.0C	(A) ≥ 1.0C

Maintenance & Cautions

Cycle service
※ Avoid battery over discharge, especially battery series connection use.
※ Charged with recommend voltage, ensure battery can be full recharged.
In general, recharge capacity should be 1.1-1.15 times discharge capacity.
※ Effect of temperature on cycle charge voltage: -4mV/°C/Cell.
※ There are a number of factors that will affect the length of cyclic service.
The most significant are depth of discharge, ambient temperature, discharge rate, and the manner in which the battery is recharged.
Generally speaking, the most important factors is depth of discharge.

Charge the batteries at least once every six months, if they are stored at 25°C.

Charging Method:

Constant Voltage	-0.2Cx2h+2.4~2.45V/Cellx24h, Max. Current 0.3CA
Constant Current	-0.2Cx2h+0.1CAx12h
Fast	-0.2Cx2h+0.3CAx4.0h