



RL21500D (2V1500Ah)

RL21500D is AGM Deep cycle battery with 18 years floating design life, specially designed for frequent cyclic discharge usage. By using strong grid and specific paste plate, it makes battery have 30% more cyclic life time than standby series. It is applicable for solar energy system, golf cart, electric wheelchair, etc..



Specification

Cells Per Unit	1
Voltage Per Unit	2
Capacity	1500Ah@10hr-rate to 1.80V per cell @25°C
Weight	Approx. 96.0 Kg
Max. Discharge Current	6000 A (5 sec)
Internal Resistance	Approx.0.5 mΩ
Operating Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C±5°C
Float charging Voltage	2.27 to 2.3 VDC/unit Average at 25°C
Recommended Maximum Charging Current Limit	300 A
Equalization and Cycle Service	2.43 to 2.47 VDC/unit Average at 25°C
Self Discharge	RITAR Valve Regulated Lead Acid (VRLA) batteries can be stored for more than 6 months at 25°C. Self-discharge ratio less than 3% per month at 25°C. Please charge batteries before using.
Terminal	Thread insert & Bolt (F10)
Container Material	A.B.S. (UL94-HB) , Flammability resistance of UL94-V1 can be available upon request.



MH28539






G4M20206-0910-E-16




ISO9001:2000 Certificate

Dimensions

Unit: mm Dimension: 401(L)×352(W)×338(H)



Terminal F10



Constant Current Discharge Characteristics: A (25°C)


F.V/Time	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	6HR	8HR	10HR
1.60V	2037	1502	966.6	574.6	427.9	341.1	287.3	241.3	194.8	162.8
1.65V	1937	1442	924.7	553.6	410.0	329.2	275.3	235.5	186.0	160.0
1.70V	1806	1359	906.7	544.6	401.0	326.2	272.3	229.7	183.1	157.1
1.75V	1603	1223	834.9	514.7	380.0	308.2	260.3	218.0	177.3	154.2
1.80V	1380	1114	787.0	490.8	365.1	305.2	251.4	215.1	174.4	151.3
1.85V	1167	1003	727.2	463.8	347.1	281.3	239.4	203.5	165.7	141.0

Constant Power Discharge Characteristics: W (25°C)


F.V/Time	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	6HR	8HR	10HR
1.60V	3565	2737	1770	1064	797.5	641.1	542.9	465.5	370.6	314.3
1.65V	3472	2723	1764	1049	781.8	631.6	536.8	459.6	367.5	311.3
1.70V	3280	2577	1732	1034	769.9	629.1	532.0	448.9	361.8	306.5
1.75V	2922	2322	1595	978.5	742.3	597.5	509.7	426.8	350.4	301.6
1.80V	2529	2119	1504	934.5	711.6	594.8	493.1	421.7	344.8	290.8
1.85V	2156	1910	1390	884.6	677.9	550.9	470.6	399.5	327.6	280.0

All mentioned values are average values.

Life characteristics of cyclic use




Storage characteristic



Charge characteristic curve for cyclic use



Discharge characteristic curve



Capacity Factors With Different Temperature

Battery Type		-20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
GEL Battery	6V&12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%
	2V	60%	75%	85%	88%	92%	99%	100%	103%	105%	106%
AGM Battery	6V&12V	46%	66%	76%	83%	90%	98%	100%	103%	107%	109%
	2V	55%	70%	80%	85%	92%	99%	100%	104%	108%	110%

Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75V	1.70V	1.60V
Discharge Current (A)	(A) ≤ 0.2C	0.2C < (A) < 1.0C	(A) ≥ 1.0C

Maintenance & Cautions

Cycle service
※ Avoid battery over discharge, especially battery series connection use.
※ Charged with recommend voltage, ensure battery can be full recharged.
In general, recharge capacity should be 1.1-1.15 times discharge capacity.
※ Effect of temperature on cycle charge voltage: -4mV/°C/Cell.
※ There are a number of factors that will affect the length of cyclic service.
The most significant are depth of discharge, ambient temperature, discharge rate, and the manner in which the battery is recharged.
Generally speaking, the most important factors is depth of discharge.

Charge the batteries at least once every six months, if they are stored at 25°C.

Charging Method:

Constant Voltage	-0.2Cx2h+2.4~2.45V/Cellx24h, Max. Current 0.3CA
Constant Current	-0.2Cx2h+0.1CAx12h
Fast	-0.2Cx2h+0.3CAx4.0h